

Technical Data Sheet



Product Code : 21W Grey

Description : Grey pressed woollen felt.

Construction : 75% min wool content
Fibre Type : 25% other fibres

Designation : BS4060 2006 A75/8W

Product Performance Characteristics

Weight	Density DIN 61200	Width ISO 3932	Thickness DIN 61206	Tensile Strength	PH	Max Shrinkage in Water	Max Swelling in Water	Min. Oil Retention	Flammability FMVSS-302 / DBL 5307	Tolerances
210gmm/ square metre/ 1mm thick	0.21g/cm ³	180cm	3mm 6mm 10mm 15mm	Min 1000 kn/m ²	Neutral 5 to 8	10%	20%	120%	≤ 100mm/min	As BS4060 2006 Table 2

Storage : Store in clean dry conditions preferably off floor level in seal bags. Mildew can occur if felts become damp and unproofed.

This information is correct at time of press and is subject to the most recent product analysis. All data shown as mean values. The above data is given for information only and does not constitute a guide to the use of our products.

Anglo Technical Textiles
Tong Lane Whitworth
Lancashire OL12 8BG
Tel: 0845 835 0210
Email: info@anglotechnicaltextiles.co.uk
www.anglotechnicaltextiles.co.uk