

# Iron-on interlining



# ANGLO

TECHNICAL TEXTILES


**Quality Ref: 8055**


Description	A heavy weight, firm handle, fusable interlining
Application	Ladies and gents coats, waistbands
Composition	80g/m <sup>2</sup> , 100% viscose wet laid
Coating	18g/m <sup>2</sup> 100% polythene, sinter coating
Colour	White
Colour stability	Fast and stable to HLCC4
Width	100cm-1500mm
Length	50m/100m

### Fusing conditions

Temperature	Hand Iron	Flat Bed Press	Continuous
	Hot	150°C	150°C
Time - Seconds	10-12	10-12	10-12
Pressure	Continuous	300g/cm <sup>2</sup>	3Kg/m <sup>2</sup>

**After Care**

**Washing Symbol**   
 A number will indicate the maximum temperature (degrees C) which should be employed. A cross indicates that washing is not recommended.

**Dry-cleaning symbol**   
 A letter in the circle will indicate the type of dry-cleaning fluid to be used. A cross indicates that the interlining is not recommended for dry-cleaning.

**Dry-cleaning fluids**  
 P Perchloroethylene, white spirit  
 F White spirit or Arklone

**Fusing recommendations**

**Temperature**  
 The recommended temperature is the heat which is available for fusing between the platens or rollers of a fusing press rather than the reading on the temperature dial. Should a digital pyrometer not be available to check the temperature, the use of thermo papers is recommended.

**Pressure**  
 The majority of conveyor-type electrically heated presses indicate the pressure as line pressure or dial pressure. The equivalent pressure exerted on the press bed (buck pressure) is calculated as roughly one-twentieth of the line pressure. For other types of press, operators should consult their press supplier for conversion factors.

**Time**  
 The specified fusing time is that in which fusing is actually taking place, i.e when the platens are closed (flat bed) or when the garment is in the main heating zone (conveyor type). The overall time should therefore be adjusted by the timing dial to allow for these conditions.

**Fusing records**  
 For optimum results, it is essential that press operators carry out periodic checks on each of the above three parameters and a record kept of all readings taken.

**Testing**  
 Fusing conditions are given as a guide and should be varied to suit individual presses and top fabrics. Tests to evaluate the compatibility of the interlining and top fabric, both before and after washing and/or dry-cleaning, are recommended before proceeding to bulk production.

### After Care

